

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT • 2 = GOOD
3 = SECOND-RATE • 4 = UNADVISABLE
— = NO INFORMATION AVAILABLE
B = BOILING • C = HOT
Ta = ROOM TEMPERATURE

MEDIA / MEDIEN	CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	ASI 304 18/8 CF8 1.4301	ASI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216/MSB	6625 66G40	CW617N CW602N
A							
Acetaldehyde		Ta	1	1	3	3	—
Acetilene		+20	1	1	1	1	4
Acetic Acid	10%	+20	1	1	4	4	2
Acetic Acid	10%	B	2	4	4	4	4
Acetic Acid	20-80%	+20	1	2	4	4	4
Acetic Acid	80%	B	2	2	4	4	4
Acetic Acid (vapours)	30%	C	3	3	4	4	4
Acetic Anhydride		B	2	2	3	3	3
Acetic Ester	Concentrated	+20	1	1	2	2	—
Acetic Solvents		Ta	1	1	1	2	—
Acetone		B	1	1	2	2	1
Acido Cresilico		+20	1	1	2	2	2
Acido Idrofluorosilicico		Ta	3	3	4	4	2
Acrylonitrile		Ta	1	1	1	1	—
Alcool Diacetone		Ta	1	1	1	1	—
Alum	10%	B	2	2	4	4	2
Alum	saturated	B	3	2	4	4	—
Aluminium Chloride	25%	+20	4	3	4	4	4
Aluminium (Chloride)	25%	+20	4	3	4	4	—
Aluminium (Chloride)	25%	B	4	4	4	4	—
Aluminium (Fluoride)	5%	+20	4	3	4	4	—
Aluminium Sulfate		+20	2	2	4	4	—
Aluminium Sulfate		B	3	2	4	4	—
Aluminum Sulphate		Ta	2	1	3	3	3
Ammines		+20	1	1	1	1	—
Ammonia	concentrated	+20	1	1	2	2	1
Ammonia	acquarosa	Ta	1	1	1	1	4
Ammonia	gaseous	C	4	4	3	3	—
Ammonium Bicarbonate		Ta	2	2	3	3	—
Ammonium Carbonate		+20	2	2	2	2	—
Ammonium Carbonate		Ta	2	2	2	2	—
Ammonium Chloride	10%	+20	2	2	3	3	4
Ammonium Chloride	10%	+20	2	2	3	3	—
Ammonium Chloride	10%	B	3	2	4	4	—
Ammonium Disulphate		+20	1	1	3	3	—
Ammonium Hydroxide	Concentrated	C	1	1	2	2	—
Ammonium Hydroxide		Ta	1	1	2	2	—
Ammonium Hydroxide		C	1	1	2	2	4
Ammonium Monophosphate		+20	1	1	4	4	—
Ammonium Monophosphate		+20	1	1	4	4	—
Ammonium Nitrate		+20	2	2	2	2	—
Ammonium Nitrate	Saturated	B	2	2	3	3	—
Ammonium Nitrate		+20	2	2	2	2	4
Ammonium Persulphate	5%	+20	2	2	4	4	—
Ammonium Phosphate		Ta	2	2	4	4	—
Ammonium Sulphate	5%	+20	3	2	3	3	—
Ammonium Sulphate	10%	B	4	3	4	4	—
Ammonium Sulphate	Saturated	B	4	3	4	4	—
Ammonium Sulphate		+20	3	2	3	3	4
Ammonium Trisulphate		+20	2	1	2	2	—
Amyl Acetate	concentrated	+20	2	2	2	2	—
Amyl Acetate		Ta	2	2	3	3	2
Amyl Alcohol	concentrated	+20	1	1	4	4	1
Aniline	3%	+20	1	1	2	2	3
Aniline	Concentrated	+20	2	2	2	2	3
Aniline (dyes)		Ta	1	1	3	3	3
Animal Oil		Ta	1	1	1	1	—
Antimony Trichloride		+20	4	4	4	4	—
Antimony Trichloride		Ta	4	4	4	4	—
Apple Juice		Ta	2	2	4	4	4
Asphalt		Ta	1	1	2	2	1
B							
Barium Chloride	Saturated	+20	3	2	3	3	3
Barium Chloride	Water sol.	C	4	3	4	4	3
Barium Carbonate		Ta	2	2	2	2	1
Barium Chloride	5%	+20	2	2	3	3	4
Barium Hydroxide		Ta	2	2	3	3	2
Barium Sulphate	Saturated	+20	3	2	2	2	1

1 = SEHR GUT • 2 = GUT
3 = NICHT VORGESCHLAGEN • 4 = SCHLECHT
— = FEHLENDE INFORMATIONEN
B = SEHR HEISS • C = HEISS
Ta = UMGEBUNGSTEMPERATUR

MEDIA / MEDIEN	CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	ASI 304 18/8 CF8 1.4301	ASI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216/MSB	6625 66G40	CW617N CW602N
C							
Barium Sulphate		+20	2	2	2	2	2
Barium Sulphite		Ta	2	2	3	3	1
Benzaldehyde		Ta	1	1	1	1	—
Benzoic Acid		+20	2	2	2	2	2
Benzol		C	2	2	2	2	1
Borax		+20	1	1	2	2	1
Boric Acid	5%	C	2	2	4	4	2
Brine		Ta	2	2	3	3	2
Bromine		+20	4	4	4	4	4
Butadiene		Ta	1	1	1	1	1
Butane		Ta	1	1	1	1	1
Butyric Acid	5%	+70	2	2	3	3	4
Butyl Alcohol		Ta	1	1	2	2	1
Butylene		ta	1	1	1	1	—
Butyl Acetate		+20	2	2	1	1	—
C							
Calcium Bisulphite		+20	3	2	4	4	2
Calcium Bisulphite		+20	3	2	4	4	2
Calcium Carbonate		+20	2	2	2	2	1
Calcium Carbonate		+20	2	2	2	2	1
Calcium Chloride		+20	3	2	3	3	4
Calcium Chloride	Diluted	+20	3	2	3	3	4
Calcium Chloride	Concentrated	+20	4	3	3	3	4
Calcium Chloride	Concentrated	B	4	4	4	4	4
Calcium Hydroxide	5%	+20	2	2	2	2	2
Calcium Hydroxide	10%	B	2	2	4	4	2
Calcium Hydroxide	50%	B	4	2	4	4	2
Calcium Hypochlorite	2%	+20	3	3	4	4	4
Calcium Hydroxide		Ta	1	1	1	1	—
Calcium Hydroxide		+20	2	2	2	2	2
Calcium Hypochlorite		+20	3	3	4	4	4
Calcium Sulphate		Ta	2	2	3	3	1
Calcium Sulphate	Saturated	+20	2	2	2	2	—
Carbolic Acid		B	2	2	3	3	—
Carbonic Acid	saturated	+20	2	2	4	4	—
Carbon Dioxide		Ta	1	1	1	1	1
Carbon Disulphide		+20	2	2	2	2	2
Carbon Disulphide		Ta	2	2	2	4	1
Carbon Monoxide		B	1	1	1	1	—
Carbon Tetrachloride		+20	2	2	2	2	3
Carbon Tetrachloride		B	3	3	4	4	3
Carbon Tetrachloride	Dry	Ta	1	1	2	2	3
Carbon Tetrachloride	Wet	Ta	2	2	4	4	4
Caustic Soda	5%	+20	2	2	2	2	—
Caustic Soda	20%	B	1	1	2	2	—
Caustic Soda	50%	B	2	2	3	3	—
Caustic Soda	75%	B	3	3	4	4	—
Chlorinated Solvents	Dry	Ta	2	2	3	3	—
Chloroacetic Acid		+20	4	4	4	4	4
Chlorobenzene	Concentrated	+20	1	1	1	1	—
Chloroform		+20	1	1	1	1	1
Chlorous Acid		+20	4	4	4	4	4
Chlorosulfonic Acid	10%	+20	3	2	4	4	3
Chlorosulfonic Acid	concentrated	+20	2	2	4	4	3
Chromic Acid	5%	+20	2	2	2	2	4
Chromic Acid	50% com.	B	4	4	4	4	4
Citric Acid	5%	+20	1	1	4	4	3
Citric Acid	15%	B	2	2	4	4	3
Citric Acid	concentrated	B	4	2	4	4	3
Colophony		Ta	1	1	4	4	—
Coke-oven Gas		Ta	1	1	2	2	—
Copper Acetate		Ta	1	1	4	4	—
Copper Acetate	Saturated	+20	2	2	4	4	—
Copper Chloride	19%	+20	3	2	3	2	4
Copper Chloride	1%	+20	3	2	4	4	—
Copper Chloride	5%	B	4	4	4	4	—
Copper Nitrate	5%	+20	1	1	4	4	3
Copper Nitrate	5%	220	1	1	4	4	—
Copper Nitrate	50%	C	2	2	4	4	—

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT • 2 = GOOD 3 = SECOND-RATE • 4 = UNADVISED -- = NO INFORMATION AVAILABLE B = BOILING • C = HOT Ta = ROOM TEMPERATURE							
MEDIA / MEDIEN	CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	AISI 304 CF8 1.4301	AISI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216WCB	6625 66G40	CW617N CW602N
Copper Sulphate	Saturated	+20	2	2	4	4	—
Copper Sulphate		B	2	2	4	4	4
Copper Sulphate		+20	2	2	4	4	4
Creosote		C	2	2	2	2	—
Creosote Oil		Ta	2	2	2	2	1
Cyclohexane	Ta	1	1	1	1	—	
D							
Dichloroethane		B	2	2	4	4	—
Diethylamine		Ta	1	1	1	1	—
Diethyl Ether		+20	1	1	1	2	—
Distilled water		Ta	1	1	3	3	1
E							
Epsom Salt		Ta	2	2	3	3	—
Ethane		Ta	2	2	2	2	1
Ethyl Acrylate		Ta	1	1	3	3	—
Ethyl Alcohol		B	2	2	2	2	1
Ethyl Acetate		Ta	2	2	2	2	1
Ethyl Chloride	Dry	+20	1	1	1	1	—
Ethyl Chloride		+20	1	1	1	1	2
Ethylene Glycol		+20	1	1	1	1	2
Ethylene Oxide		Ta	2	2	2	2	1
F							
Fatty Acids		B	2	2	3	3	4
Ferric Chloride	1%	+20	4	3	4	4	4
Ferric Chloride	5%	+20	4	4	4	4	4
Ferric Nitrate		Ta	3	3	4	4	4
Ferric Nitrate	5%	+20	2	2	4	4	4
Ferric Sulphate		+20	2	1	4	4	4
Ferric Sulphate	5%	B	2	2	4	4	4
Ferrous Chloride		Ta	4	4	4	4	4
Ferrous Sulphate	Saturated	+20	2	2	4	4	4
Ferrous Sulphate		+20	2	2	4	4	4
Fertilizers		Ta	2	2	2	2	—
Fish Oil		Ta	1	1	2	2	—
Fluorine	Dry	+20	2	2	4	4	—
Formaldehyde		Cold	1	1	1	2	3
Formaldehyde		Hot	3	3	4	4	3
Formic Acid	5-50%	+20	2	2	4	4	4
Formic Acid	10-50%	B	4	4	4	4	4
Formic Acid	100%	+20	3	3	4	4	4
Formic Acid	100%	B	4	4	4	4	4
Freon	Dry	Ta	1	1	1	1	1
Freon		Wet	Ta	3	3	3	3
Fuel Oil		Ta	1	1	2	2	1
Furfuraldehyde		+20	2	2	2	2	1
G							
Gallic Acid	5%	+70	2	2	4	4	—
Gas Chlorate	Dry	+20	4	3	2	2	—
Gas Chlorate		Wet	+100	4	4	4	—
Gaseous Methyl Chloride		+20	2	2	4	4	—
Gelatine		Ta	1	1	4	4	2
Glue		Ta	2	2	1	1	—
Glucose		Ta	2	2	2	2	1
Glycerol		+20	1	1	1	1	1
Glycols		Ta	2	2	2	2	—
H							
Heptane		Ta	1	1	2	2	—
Hexane		Ta	2	2	2	2	—
Hexanol		Ta	1	1	1	1	—
Hydraulic Oil		Ta	1	1	1	1	—
Hydriodic Acid (iodidrico)	diluted	+20	4	4	4	4	—
Hydrocarbons		+20	1	1	1	1	1
Hydrobromic Acid		+20	4	4	4	4	4
Hydrocyanic Acid		+20	2	2	3	3	—
Hydrochloric Acid	1%	+20	4	3	4	4	4

1 = SEHR GUT • 2 = GUT 3 = NICHT VORGESCHLAGEN • 4 = SCHLECHT -- = FEHLENDE INFORMATIONEN B = SEHR HEISS • C = HEISS Ta = UMGEBUNGSTEMPERATUR							
MEDIA / MEDIEN	CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	AISI 304 CF8 1.4301	AISI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216WCB	6625 66G40	CW617N CW602N
Hydrochloric Acid	1%	B	4	4	4	4	4
Hydrochloric Acid	5%	+20	4	4	4	4	4
Hydrochloric Acid		+20	4	4	4	4	4
Hydrofluoric Acid	concentrated	+20	4	4	4	4	4
Hydrofluoric Acid		dry	+20	3	3	3	4
Hydrofluoric Acid		wet	+20	4	4	4	4
Hydrofluoric Acid		+20	4	4	4	4	4
Hydrogen Gas	Cold	Ta	1	1	2	2	—
Hydrogen dioxide		+20	1	1	4	4	4
Hydrogen dioxide		B	2	2	4	4	4
I							
Illuminating Gas		Ta	1	1	1	1	—
Ink	Dry Wet	Ta	1	1	4	4	—
Iodine		+20	4	3	4	4	—
Iodine		+20	4	4	4	4	—
Iodoform		+20	1	1	4	4	—
Isocotane		Ta	1	1	1	1	—
Isopropyl Ether		Ta	1	1	1	2	—
Isopropyl Alcohol		Ta	2	2	2	2	—
J							
Juices		B	2	1	4	4	4
K							
Ketone		Ta	1	1	1	1	—
Kerosene		Ta	1	1	2	2	—
L							
Lactic Acid	1%	B	2	2	4	4	3
Lactic Acid	5%	+70	2	2	4	4	3
Lactic Acid	5%	B	4	2	4	4	3
Lactic Acid	5-10%	+20	2	1	4	4	3
Lactic Acid	10%	+70	3	2	4	4	3
Lactic Acid	10%	B	4	3	4	4	3
Lactic Acid	concentrated	B	4	4	4	4	3
Latex		+20	1	1	4	4	—
Latex Emulsions		Ta	1	1	2	2	—
Lead Acetate		+20	2	2	4	4	—
Lead Acetate		Ta	2	2	4	4	—
Lemon Juice		Ta	2	2	4	4	4
Linoleic Acid		Ta	1	1	2	2	—
Linseed Oil		Ta	2	2	1	1	2
Liquefied Gas (LPG)		Ta	2	2	2	2	—
Lithium		+150	1	1	2	2	—
Lubricating Oil		Ta	1	1	1	1	—
Lye		B	2	2	4	4	4
Lysol		+20	3	3	4	4	—
M							
Magnesium Chloride	5%	+20	2	2	4	4	4
Magnesium Chloride	5%	C	4	4	4	4	4
Magnesium Chloride	10-30%	+20	3	2	4	4	4
Magnesium Chloride	Saturated	+20	3	2	4	4	4
Magnesium Chloride		5%	+20	2	2	4	4
Magnesium Disulphate		Ta	1	1	2	2	—
Magnesium Hydroxide		C	1	1	2	2	2
Magnesium Oxide		+20	2	2	2	2	—
Magnesium Sulphate		+20	2	2	2	2	3
Magnesium Sulphate		+20	2	2	2	2	3
Maleic Acid		Ta	2	2	2	2	—
Malic Acid		C	2	2	4	4	—
Mercury		+150	3	3	2	2	4
Mercury	+500	4	4	4	4	4	4
Mercury Bichloride	2%	+20	4	4	4	4	4
Mercury Cyanide		+20	2	2	4	4	4
Mercury Cyanide		+20	2	2	4	4	—
Mercuric Chloride		Ta	4	3	4	4	—
Methane		Ta	2	2	2	2	1
Methyl Acetate		Ta	1	1	2	2	—

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT • 2 = GOOD
3 = SECOND-RATE • 4 = UNADVISABLE
— = NO INFORMATION AVAILABLE
B = BOILING • C = HOT
Ta = ROOM TEMPERATURE

MEDIA / MEDIEN	CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	AISI 304 18/8 CF8 1.4301	AISI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216/WCB	GG25 6GG40	CW617N CW602N
Methyl Alcohol		B	3	2	2	2	1
Methylacetone		Ta	1	1	2	2	—
Methylamine		Ta	1	1	2	2	—
Methyl Chloride	+20	2	2	4	4	2	—
Methylene Chloride		Ta	1	1	2	2	2
Methyl Formate		Ta	2	2	3	3	—
Milk	+20	1	1	4	4	2	—
Mineral Naphtha	+20	2	2	2	2	2	—
Mineral Oil		Ta	1	1	2	2	1
Mineral water		Ta	2	2	3	3	2
Mixed Acid-turpentine	+20	4	4	4	4	4	—
Muriatic Acid	+20	4	3	4	4	4	—
N							
Naphthalene		Ta	2	2	1	1	—
Natural Gas (Biogas)		Ta	1	1	3	3	1
Neon	+20	2	2	2	2	—	—
Nickel Chloride	+20	3	2	4	4	3	—
Nickel Chloride	+20	3	2	4	4	3	—
Nickel Sulphate	C	3	2	4	4	3	—
Nickel Sulphate	C	3	2	4	4	3	—
Nickel Nitrate		Ta	2	2	4	4	—
Nicotinic Acid		Ta	1	1	2	2	—
Nitric Acid	5-50%	+20	1	1	4	4	4
Nitric Acid	10-50%	B	2	3	4	4	4
Nitric Acid	85%	+20	2	2	2	2	4
Nitric Acid	85%	C	2	3	4	4	4
Nitric Acid	concentrated	+20	2	2	2	2	4
Nitric Acid	concentrated	B	3	3	4	4	4
Nitric Acid	anhydrous	Ta	1	1	1	1	4
Nitrobenzene		Ta	2	2	2	2	—
Nitrogen		Ta	1	1	1	1	1
Nitrous Acid	5%	+20	2	2	4	4	—
Nitrous Gases		Ta	1	1	2	2	—
Nitrous Oxide		Ta	2	2	2	2	—
O							
Oil		Ta	1	1	2	2	2
Oleic Acid	crude	+20	2	2	3	3	—
Oleum		Ta	2	2	2	2	—
Olive Oil		Ta	1	1	2	2	3
Oxalic Acid	5%	C	3	3	4	4	—
Oxalic Acid	10%	+20	2	2	3	3	—
Oxalic Acid		B	4	4	4	4	—
Oxalic Acid	saturated	+20	2	2	3	3	—
Oxalic Acid	saturated	B	4	4	4	4	—
Oxygen	Cold		1	1	2	2	1
Oxygen		+250	2	2	2	2	—
Ozone	Dry	Ta	1	1	3	3	—
Ozone	Wet	Ta	1	1	1	1	—
P							
Paint Varnish		Ta	1	1	3	3	—
Palm Oil		Ta	2	2	3	3	—
Palmitic Acid		+20	2	2	3	3	3
Paraformaldehyde		Ta	2	2	2	2	—
Paraffin wax		Ta	1	1	1	1	1
Pentane		Ta	1	1	2	2	—
Perchloroethylene		Ta	1	1	2	2	3
Peroxide		Ta	2	2	4	4	4
Petrol		Ta	1	1	1	1	1
Petrol (Crude)		+20	1	1	3	3	1
Phenol		B	2	2	3	3	—
Phosphoric Acid	C.P.1%	+20	2	2	4	4	4
Phosphoric Acid	5%	+20	2	2	4	4	4
Phosphoric Acid	10%	+20	3	2	4	4	4
Phosphoric Acid	20-45%	B	4	3	4	4	4
Phosphoric Acid	45-85%	+20	4	2	4	4	4
Phosphoric Acid	85%	B	4	4	4	4	4
Phthalic Acid		Ta	2	2	3	3	—

1 = SEHR GUT • 2 = GUT
3 = NICHT VORGESCHLAGEN • 4 = SCHLECHT
— = FEHLENDE INFORMATIONEN
B = SEHR HEISS • C = HEISS
Ta = UMGEBUNGSTEMPERATUR

MEDIA / MEDIEN	CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	AISI 304 18/8 CF8 1.4301	AISI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216/WCB	GG25 6GG40	CW617N CW602N
Phthalic Anhydride			2	2	3	3	—
Picric Acid	water sol.	+20	2	2	3	3	4
Potassium Bichromate		+20	2	2	3	3	—
Potassium Bisulphite		Ta	2	2	4	4	—
Potassium Bromide		+20	3	2	4	4	—
Potassium Bromide		+20	3	2	4	4	—
Potassium Carbonate	1%	+20	2	2	2	2	3
Potassium Carbonate	1%	+20	2	2	2	2	—
Potassium Chlorate		+20	2	2	2	2	—
Potassium Chloride	1-5%	+20	3	2	4	4	3
Potassium Chlorate		+20	2	2	2	2	4
Potassium Chloride	1-5%	+20	3	2	4	4	4
Potassium Chloride	1-5%	B	4	4	4	4	4
Potassium Cyanide		+20	2	2	2	2	4
Potassium Cyanide		+20	2	2	2	2	4
Potassium Dichromate		+20	2	2	3	3	4
Potassium Diphosphate		Ta	1	1	1	1	—
Potassium Disulphite	Saturated	+20	2	2	3	3	2
Potassium Ferricyanide		Ta	2	2	3	3	4
Potassium Ferricyanide	5%	+20	2	2	3	3	4
Potassium Hydroxide	5%	+20	2	2	2	2	4
Potassium Hypochlorite		+20	4	3	4	4	—
Potassium Iodide	2%	Ta	2	2	3	3	—
Potassium Nitrate	1-5%	+20	2	2	2	2	2
Potassium Nitrate	1-5%	C	2	2	2	2	—
Potassium Permanganate		+20	1	1	1	1	—
Potassium Permanganate		+20	1	1	1	1	—
Potassium Sulphate	1-5%	+20	2	2	2	2	2
Potassium Sulphate	Saturated	+20	2	2	3	3	—
Potassium Sulphate		+20	2	2	2	2	2
Potassium Sulphite		Ta	1	1	2	1	2
Propane		Ta	2	2	2	2	1
Propanol		Ta	1	1	2	2	—
Propylene Glycol		Ta	2	2	2	2	—
Propionic Acid		+20	2	2	4	4	—
Prussic Acid		+20	2	2	3	3	—
Pyrogalllic Acid		+20	2	2	2	2	—
Pyroligneous Acid		+20	1	1	4	4	—
Q							
Quinine Bisulphate	Dry	+20	2	2	4	4	—
R							
Resins		Ta	1	1	3	3	—
S							
Sal Ammoniac		+20	2	2	3	3	—
Salicylic Acid		+20	2	2	4	4	—
Sea water		+20	2	2	4	4	3
Shellac		Ta	1	1	1	1	—
Silver Bromide		+20	3	2	4	4	—
Silver Chloride		+20	4	4	4	4	—
Silver Nitrate		+20	2	2	4	4	—
Silver Nitrate		+20	2	2	4	4	4
Sludge		Ta	1	1	2	2	—
Soap		+20	2	2	2	2	2
Sodium Acetate	Wet	+20	2	2	3	3	—
Sodium Acetate		Ta	2	2	3	3	—
Sodium Bicarbonate		+20	2	2	3	3	3
Sodium Bicarbonate		+20	2	2	3	3	3
Sodium Bisulphite		Ta	1	1	4	4	2
Sodium Borate		Ta	2	2	3	3	—
Sodium Bromide		Ta	2	2	3	4	—
Sodium Carbonate	5%	+70	2	2	2	2	—
Sodium Carbonate		+20	2	2	2	2	4
Sodium Chlorate	10%	+20	2	2	3	3	—
Sodium Chloride	20%	+20	2	2	3	3	—
Sodium Chloride	Saturated	B	3	2	4	4	—
Sodium Chlorate		+20	2	2	3	3	4
Sodium Chloride	5%	+20	2	2	3	3	3

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT • 2 = GOOD 3 = SECOND-RATE • 4 = UNADVISABLE -- = NO INFORMATION AVAILABLE B = BOILING • C = HOT Ta = ROOM TEMPERATURE		CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	AISI 304 CF8 1.4301	AISI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216/WCB	GG25 GGG40	CW617N CW602N
MEDIA / MEDIEN								
Sodium Cyanide			+20	2	2	2	2	4
Sodium Cyanide			+20	2	2	2	2	—
Sodium Disulphate			+20	2	2	4	4	2
Sodium Disulphate			+20	2	2	4	4	—
Sodium Disulphite			+20	2	2	2	2	2
Sodium Disulphite			C	2	2	3	3	2
Sodium Fluoride			Ta	2	2	4	4	—
Sodium Fluoride	5%		+20	2	2	4	4	—
Sodium Hydroxide			+20	1	1	1	1	—
Sodium Hypochlorite			Ta	3	3	4	4	4
Sodium Hypochlorite			+20	2	2	4	4	4
Sodium Hypochlorate	5%		+20	4	3	4	4	4
Sodium Hyposulphite			+20	2	2	4	4	4
Sodium Metaphosphate			Ta	1	1	2	2	4
Sodium Metasilicate	Cold		1	1	3	3	—	—
Sodium Metasilicate			C	1	1	4	4	—
Sodium Nitrate			+20	1	1	2	2	—
Sodium Nitrate			Ta	2	2	2	2	3
Sodium Perborate			Ta	2	2	2	2	—
Sodium Peroxide			Ta	2	2	3	3	4
Sodium Phosphate			Ta	2	2	3	3	—
Sodium Silicate			Ta	2	2	2	2	2
Sodium Silicate			C	2	2	3	3	2
Sodium Silicate			Ta	2	2	2	2	—
Sodium Sulphate	Saturated		+20	3	2	2	2	2
Sodium Sulphate			+20	3	2	2	2	2
Sodium Sulphite	10%		+65	3	2	2	2	2
Sodium Sulphite	10%		B	3	2	4	4	2
Sodium Sulphide	Saturated		+20	2	2	2	2	2
Sodium Trisulphate	20%		+20	2	2	4	4	—
Sodium Thiosulphate			Ta	1	1	2	2	—
Soft water			Ta	1	1	3	3	4
Solvent			Ta	1	1	2	2	1
Spirit Vinegar			+20	1	1	4	4	—
Starci			Ta	2	2	3	3	—
Stannic Chloride	5%		+20	4	3	4	4	—
Stannic Chloride	5%		B	4	4	4	4	—
Stannic Chloride	5%		+20	4	3	4	4	—
Stannous Chloride	Saturated		+20	4	3	4	4	—
Stearic Acid			+20	2	1	3	3	3
Strontium Nitrate			+20	1	1	4	4	—
Styrene			Ta	1	1	1	1	—
Suds (Stearate)			Ta	1	1	1	2	—
Sugary Juices in general			+70	2	2	4	4	4
S Sulphur	Dry and liquefied		+230	2	2	2	2	4
S Sulphur	Wet and liquefied		+230	3	2	4	4	4
Sulphuric Anhydride	Dry		Ta	1	1	2	2	2
Sulphidric Acid	dry		+20	1	1	1	1	—
Sulphidric Acid	wet		+20	3	2	3	3	—
Sulphuric Acid	5%		+20	3	2	4	4	4
Sulphuric Acid	5%		B	4	3	4	4	4
Sulphuric Acid	10%		+20	4	3	4	4	4
Sulphuric Acid	10%		B	4	4	4	4	4
Sulphuric Acid	50%		+20	4	4	4	4	4
Sulphuric Acid	50%		B	4	4	4	4	4
Sulphuric Acid	concentrated		+20	2	2	2	2	4
Sulphuric Acid	concentrated		B	4	4	4	4	4
Sulphuric Acid	fuming		+20	3	2	3	3	4
Sulphur Chloride			Ta	3	2	4	4	—
Sulphur Dioxide	Dry		+250	2	2	2	2	1
Sulphur Dioxide	Dry		+230	2	2	2	2	4
Sulphur Dioxide	Wet		+20	3	2	4	4	4
Sulphurous Acid	saturated		+20	4	2	4	4	3
Syngas			Ta	2	2	2	2	—
T								
Tannic Acid			+20	2	2	4	4	2
Tar			Ta	1	1	1	1	2
Tartaric Acid	10%		+20	1	1	4	4	3
Tartaric Acid	10%		C	3	2	4	4	3

1 = SEHR GUT • 2 = GUT 3 = NICHT VORGESCHLAGEN • 4 = SCHLECHT -- = FEHLENDE INFORMATIONEN B = SEHR HEISS • C = HEISS Ta = UMGEBUNGSTEMPERATUR		CONCENTRATION PROZENT	TEMPERATURE °C TEMPERATUR °C	AISI 304 CF8 1.4301	AISI 316 18/8/2 CF8M 1.4401-1.4408	CARBON STEEL AC. AL CARBONIO A105/A216/WCB	GG25 GGG40	CW617N CW602N
MEDIA / MEDIEN								
Tetraethyl Lead			Ta	2	2	3	3	—
Titanium Tetrachloride	Wet		+20	4	4	4	4	—
Tomato Juice			Ta	1	1	3	3	4
Toluene			Ta	1	1	1	1	1
Tributyl Phosphate			Ta	1	1	1	1	—
Trichloroethylene	Dry		Ta	2	2	2	3	1
Trichloroacetic Acid			+20	4	4	4	4	3
Tung Oil			Ta	2	2	3	3	—
Turpentine			+20	1	1	1	1	2U
U								
Urea			Ta	2	2	3	3	—
Uric Acid	concentrated		+20	2	2	4	4	—
V								
Varnish			+20	1	1	3	3	1
Varnish			C	2	2	4	4	1
Vaseline			Ta	2	2	3	3	—
Vinegar (vapors)			Ta	2	2	4	4	—
Viscose			Ta	2	2	2	2	—
W								
Waste water			+20	2	2	3	3	—
Wax			Ta	1	1	1	1	—
Wax Emulsions			Ta	1	1	1	1	—
X								
Xylene	Dry		Ta	1	1	2	2	—
Z								
Zinc Chloride	5%		+20	3	2	4	4	—
Zinc Chloride	5%		B	4	3	4	4	—
Zinc Chloride	5%		+20	3	2	4	3	4
Zinc Hydrosulphite			Ta	1	1	1	1	—
Zinc Sulphate	5%		+20	2	1	2	2	2
Zinc Sulphate	25%		B	3	2	4	4	2
Zinc Sulphate			Ta	2	2	4	4	4

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT 2 = GOOD 3 = INSUFFICIENT 4 = UNADVISABLE — = NO INFORMATION AVAILABLE	DELRIN	EPDM	NBR	NBR	VITON	PTFE
A						
Acetaldehyde	2	—	4	4	1	
Acetal	—	—	—	—	1	
Acetamide	—	1	2	2	1	
Acetate Solvent	—	—	4	4	1	
Acetilene	1	1	2	2	1	
Acetic Acid 10-20%	4	1	1	1	1	
Acetic Acid 50%	4	—	1	1	1	
Acetic Acid 80%	4	1	2	2	1	
Acetic Anhydride	4	—	4	4	1	
Acetylene Chloride	—	—	4	1	1	
Acetoacetato di Etile	—	—	4	4	1	
Acetofenone	—	—	4	4	1	
Acetone	1	1	4	4	1	
Acetone 50% water	—	—	4	—	1	
Acetonitrile	—	—	—	—	1	
Acid Chloric 20%	—	—	4	4	1	
Acid Laisileico	—	—	2	2	1	
Acido Cresilico	4	—	4	1	1	
Acrylonitrile	—	—	4	4	1	
Adipic Acid	—	—	4	—	1	
Air	—	1	1	1	1	
Alumed Chrome	—	1	2	2	1	
Alumed Potassium	—	1	2	2	1	
Alumed Potassium Sulphate	—	1	—	—	1	
Alumina	—	1	1	2	1	
Aluminium Chloride	1	1	2	2	1	
Aluminium Fluoride	—	1	2	2	1	
Aluminium Hydroxide	1	1	2	2	1	
Aluminium Nitrate	—	1	2	2	1	
Aluminium Sulphate	1	1	2	2	1	
Alum (All. Potassium Sulphate)	1	—	1	1	1	
Amyl Alcohol	1	1	—	—	1	
Amyl Acetate	1	4	4	4	1	
Ammonium Acetate	—	1	4	—	1	
Ammonia (Anhydrous)	—	1	2	4	1	
Ammonia (Gas)	—	—	2	4	1	
Ammonium Chloride	3	1	2	2	1	
Ammonium Sulphate	1	1	2	4	1	
Ammonium Sulphite 50°C	—	—	1	—	1	
Ammonium Sulphide	—	1	2	4	1	
Ammonium Hydroxide	—	1	2	2	1	
Ammonium Fluoride 25%	—	1	—	—	1	
Ammonium Phosphate	—	1	2	2	1	
Ammonium Metaphosphate	—	—	2	2	1	
Ammonium Nitrate	1	1	2	4	1	
Ammonium Oxalate	—	1	—	—	1	
Ammonium Bicarbonate	3	1	—	—	1	
Ammonium Bifluoride	—	1	—	—	1	
Ammonium Carbonate	3	1	2	2	1	
Amyl Chloride 77°C	—	—	4	1	—	
Anhydrous Formic Acid	4	—	4	2	1	
Aniline	1	4	4	1	1	
Aqua Regia	—	—	4	1	1	
Arsenic Acid	—	1	2	2	1	
Artificial Gas	—	—	2	—	1	
Asphalt	1	—	4	1	1	
1 = SEHR GUT 2 = GUT 3 = NICHT VORGESCHLAGEN 4 = SCHLECHT — = FEHLENDE INFORMATIONEN	DELRIN	EPDM	NBR	NBR	VITON	PTFE
B						
Barium Carbonate	—	1	—	—	1	
Barium Chloride	1	1	2	2	1	
Barium Hydroxide	—	1	2	2	1	
Barium Nitrate	—	1	2	2	1	
Barium Sulphate	—	1	2	2	1	
Barium Sulphide	—	—	2	2	1	
Beer	—	—	2	2	1	
Benzaldehyde	—	—	4	4	1	
Benzene, Benzol	—	—	4	1	1	
Benzoic Acid	—	1	4	2	1	
Benzyl Alcohol	—	—	4	1	1	
Benzyl Chloride	—	—	4	—	1	
Black Liquor	—	—	1	2	1	
Borax	1	1	2	2	1	
Boric Acid	1	1	2	2	1	
Brine	—	2	1	—	1	
Bromine Water	—	—	4	1	1	
Butyl Acetate	—	—	—	—	1	
Butyl Alcohol	1	1	4	1	1	
Butyric Acid	1	4	4	—	1	
Butyl Chloride	—	—	—	—	1	
Butyl Phenol	—	—	—	—	1	
Butyl Phthalate	—	—	4	—	1	
Butter	—	—	1	—	1	
Butadiene	1	—	1	1	1	
Butane	1	1	4	1	1	
Butylene	1	—	4	2	1	
C						
Calcium Bisulphite	1	1	2	2	1	
Calcium Bicarbonate	—	—	—	—	1	
Calcium Carbonate	1	1	2	2	1	
Calcium Chlorate	—	—	2	2	1	
Calcium Chloride	1	1	2	2	1	
Calcium Disulphate	—	—	—	—	1	
Calcium Fluoride	—	—	—	—	1	
Calcium Hydroxide	1	1	2	2	1	
Calcium Hypochlorite	1	1	4	2	1	
Calcium Nitrate	—	1	2	2	1	
Calcium Oxide 20°C	—	—	—	—	1	
Calcium Sulphate	1	1	—	—	1	
Cane Sugar Liquor	—	1	2	2	1	
Carbolic Acid (Phenol)	—	—	4	4	1	
Carbonic Acid	4	1	2	2	1	
Carbon Bisulphide	—	—	4	2	1	
Carbon Dioxide	—	—	1	—	1	
Carbon Monoxide	—	1	2	2	1	
Castor Oil	1	1	2	2	1	
Caustic Soda	—	1	3	—	1	
Cellulose Acetate	—	1	4	4	1	
Cellosolve	—	1	4	4	1	
Cement	—	1	2	—	1	
Cereal Syrup (Glucose)	—	—	2	2	1	
Chloroacetic Acid	—	—	4	4	1	
Chloroform	1	4	4	2	1	
Chlorosulfonic Acid	—	—	—	—	1	
Chlorine Dioxide	—	—	4	—	—	
Chlorine Water	—	—	4	1	1	

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT 2 = GOOD 3 = INSUFFICIENT 4 = UNADVISABLE — = NO INFORMATION AVAILABLE	DELRIN	EPDM	EPDM XORPE XORPE	NBR	NBR	VITON	PTFE	1 = SEHR GUT 2 = GUT 3 = NICHT VORGESCHLAGEN 4 = SCHLECHT — = FEHLENDE INFORMATIONEN	DELRIN	EPDM	EPDM XORPE XORPE	NBR	NBR	VITON	PTFE
Chlorine Water	—	—	—	4	—	1		Ethyl Glycol	—	1	1	1	1	1	
Chlorobenzene	1	4	4	4	2	1		Ethylene Bromide	—	—	4	—	1	1	
Chromic Acid	4	—	2	1	1		Ethylene Chloride	—	—	4	1	1	1		
Chromic Anhydride	—	—	2	1	1		Ethylene Diamine	—	—	1	1	1	1		
Chrome Potassium Sulphate	—	—	2	—	1		Ethylene Glycol	—	1	2	1	1	1		
Citric Acid	—	1	2	2	1		Ethylene Oxide	—	—	4	4	1			
Coconut Oil	1	—	2	1	1		Epichlorohydrin	—	—	4	4	1			
Coffee	—	1	4	1	1		F								
Coke-oven Gas	—	1	4	2	1		Fats	—	4	1	—	1			
Copper Acetate	—	—	—	4	1		Fatty Acids	—	—	2	2	1			
Copper Chloride	1	1	2	2	1		Ferric Chloride	1	1	2	2	1			
Copper Nitrate	1	—	2	2	1		Ferric Nitrate 10-50%	—	1	2	2	1			
Copper Sulphate	1	1	2	2	1		Ferric Sulphate	1	1	2	2	1			
Corn Oil	1	—	4	—	1		Ferrous Chloride	1	1	2	—	1			
Cotton seeds Oil	—	—	2	1	1		Ferrous Sulphate	1	1	2	2	1			
Creosote	—	4	3	1	1		Fluorinated Hydrogen	—	—	2	2	1			
Cresol	—	—	4	4	1		Fluorine Gas	—	—	4	4	1			
Cromil Chloride	—	—	—	—	1		Fluorosilicic Acid	—	1	3	—	—			
Crotonaldehyde	—	—	—	—	1		Formaldehyde 35-50%	1	1	4	4	1			
Crude Oil	—	—	2	1	1		Formic Acid 10-85%	4	1	4	2	1			
Cyanoacetic Acid	—	—	—	—	1		Freon F 11-12	—	—	2	2	—			
Cyanogen Gas	—	1	—	—	1		Freon F 22	—	—	4	4	—			
Cyclohexane	—	4	2	2	1		Fuel Oil	1	4	2	1	1			
D							Fuel for aircrafts (JP4 or JP5)	—	4	2	1	1			
Deminerlized Water	—	1	2	2	1		Furfural	—	—	4	4	1			
Detergents	—	1	2	2	1		Furfuraldehyde	1	—	4	4	1			
Dextrine	—	—	4	4	1		G								
Dextrose	—	—	2	2	1		Gallic Acid	1	1	—	2	1			
Diacetone	—	1	4	4	1		Galvanizing Solution	—	1	2	2	1			
Diacetone Alcohol	—	—	4	—	1		Gaseous Bromine	2	4	4	—	1			
Dibutylphthalate	—	—	—	2	1		Gaseous Oxygen	1	—	4	2	1			
Dichloroethane	—	—	4	1	1		Gas Oil	—	—	2	2	1			
Dichlorobenzene max 40°C	—	—	—	2	1		Gelatine	1	—	2	2	1			
Dichloroethane	—	—	4	2	1		Glucose	1	—	2	2	1			
Dichloroethylene	—	—	4	2	1		Glue	—	1	3	—	1			
Diethyl Ether	—	—	4	4	1		Glycerol	3	—	2	1	1			
Diethyl Ether 40°C	—	—	2	4	1		Glycols 60°C	—	—	1	1	1			
Diethylcellosolve	—	—	—	—	1		Glycolic Acid	—	1	—	—	1			
Diethylamine max 40°C	—	—	4	—	1		Green Liquor	—	1	2	—	1			
Dimethyl	—	—	—	4	1		H								
Dimethylphthalate	—	—	4	1	1		Helium	—	2	2	—	1			
Dimethyl Ether	—	—	—	—	1		Heptane	—	1	2	1	1			
Dioxan	—	4	4	4	1		Hexane	—	4	2	1	1			
Diphenyl (Dowtherms)	—	—	4	1	1		Hexanol	—	—	2	1	1			
Disodium Phosphate 20°C	—	—	4	2	1		Hydraulic Fluid	—	—	2	1	1			
Distilled Water	1	1	2	2	1		Hydrobromic Acid	—	—	4	2	1			
Dry Sulphur Dioxide	4	—	4	4	1		Hydrocyanic Acid	—	1	2	2	1			
Drilling Sludge	—	4	1	—	1		Hydrochloric Acid max 50%	—	1	—	2	1			
Drilling Sludge	—	4	1	—	1		Hydrofluoric Acid max 70%	—	—	4	1	—			
Dry Sulphurized Hydrogen	—	1	—	4	1		Hydrofluoric Acid 100%	—	—	4	—	—			
Dry Sulphurized Hydrogen	—	1	—	4	1		Hydrogen Dioxide	1	1	4	1	1			
Dyes	—	4	4	—	1		Hydrogen Chloride	—	—	—	—	1			
E							Hydrogen	—	1	2	2	1			
Ethyl Acetate	1	4	4	4	1		Hydrogen Sulphide	—	—	4	4	1			
Ethyl Acrylate	—	1	2	2	1		Hydroquinone	—	1	4	2	1			
Ethyl Alcohol	1	1	3	1	1		I								
Ethyl Chloride	1	—	2	2	1		Ink	—	1	—	—				
							Industrial oils	—	—	—	—	1			

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT 2 = GOOD 3 = INSUFFICIENT 4 = UNADVISABLE — = NO INFORMATION AVAILABLE	DE LR IN	EP DM	HA LCOX XORIP	N BR	H NB R	V IT ON	P TF E
Iodoform	1	—	4	1	1	1	
Isobutyl-Methyl-Ketone	—	—	4	4	1		
Isooctane	1	4	1	1	1		
Isopropyl Alcohol	1	1	3	2	1		
Isopropyl Ether	—	—	4	4	1		
J							
Juices	1	2	2	—	1		
K							
Kerosene	—	—	2	1	1		
L							
Lactic Acid	4	—	4	2	1		
Lard Oil	—	—	1	1	1		
Lead Acetate	1	—	4	4	1		
Lead Chloride max 20°C	—	—	—	2	1		
Lead Sulphate	—	—	3	—	1		
Leaded Petrol	1	—	2	2	1		
Lemon Oil	—	2	3	—	1		
Lime	—	1	4	—	1		
Lime Sulphur	—	1	4	2	1		
Linseed Oil	1	—	2	1	1		
Liquid Chlorine	—	—	4	2	1		
Liquid Soap	—	1	2	—	1		
Lithium Bromine	—	1	2	2	1		
Lubricating Oil	—	—	2	2	1		
M							
Maleic Acid	1	1	4	2	1		
Malic Acid	1	—	2	2	1		
Manganese Chloride max 20°C	—	—	2	2	1		
Magnesium Carbonate	—	—	2	—	1		
Magnesium Chloride	1	1	2	2	1		
Magnesium Hydroxide	1	1	2	2	1		
Magnesium Nitrate	—	1	2	—	1		
Magnesium Oxide	—	2	2	—	1		
Machine Oil	—	—	—	—	1		
Magnesium Sulphate	1	1	2	—	1		
Methane	1	1	2	1	1		
Methanol	—	1	2	4	1		
Methyl Acetate	—	3	4	4	1		
Methyl Alcohol	1	1	2	4	1		
Methyl Bromine	—	—	—	2	1		
Methyl Chloride	—	—	4	2	1		
Methyl Methacrylate	—	—	2	2	1		
Methylene Chloride	—	4	4	4	1		
Methylacetone	—	2	4	4	1		
Methylcellosolve	—	—	3	4	1		
Methyl-Ethyl-Ketone	—	—	4	4	1		
Mercury	1	—	2	2	1		
Mercuric Chloride	—	1	2	2	1		
Mercuric Nitrate	—	1	—	—	1		
Milk	1	—	2	2	1		
Mineral Oil	1	—	2	2	1		
Mineral Water	1	1	2	—	1		
Mineral Naphtha (Combustible Oil)	1	4	2	1	1		
Mixed Acids (°T max 32°C)	—	1	1	1	1		
Molasses	—	1	2	2	1		
Monochlorobenzene 20°C	—	—	4	1	1		
Motor Oil	—	—	2	2	1		
n Butyl Mercaptan	—	—	—	—	1		
1 = SEHR GUT 2 = GUT 3 = NICHT VORGESCHLAGEN 4 = SCHLECHT — = FEHLENDE INFORMATIONEN	DE LR IN	EP DM	HA LCOX XORIP	N BR	H NB R	V IT ON	P TF E
N							
Naphthalene	1	—	4	2	1		
Natural Gas	1	1	2	2	1		
Nickel Ammonium Sulphate	—	—	—	—	1		
Nickel Chloride	1	1	2	—	1		
Nickel Nitrate	1	—	2	2	1		
Nickel Salt	—	—	2	—	1		
Nickel Sulphate	1	1	2	2	1		
Nicotine	—	—	—	—	1		
Nicotinic Acid	—	1	—	—	1		
Nitric Acid	4	4	4	2	1		
Nitrobenzene 25°C	—	2	4	4	1		
Nitrobenzene over 25°C	—	—	4	4	1		
Nitrogen	1	1	2	—	1		
Nitromethane	—	—	4	—	1		
Nitrous Oxide 40°C	—	—	4	3	1		
O							
Oleum	4	—	4	1	1		
Oleic Acid	1	—	1	4	1		
Oil Vegetali	—	1	2	2	1		
Olive Oil	—	2	1	1	1		
Oxalic Acid	3	1	1	2	1		
Oxygen	1	1	3	2	1		
Ozone	—	—	4	2	1		
P							
Paint Solvents	—	4	4	4	1		
Palmitic Acid	1	—	2	2	1		
Paraffin wax	1	—	2	—	1		
Perchloric Acid	—	—	4	2	1		
Perchloroethylene	—	4	4	1	1		
Persolfato di Ammonio	—	1	2	—	1		
Petrol Oils (acid or refined oils)	—	—	2	2	1		
Petrolatum (Vaseline)	—	—	—	—	1		
Phenyl Chloride (Chlorobenzene)	—	—	4	1	1		
Phenylhydrazine	—	—	4	2	1		
Phenol (Carbolic Acid)	4	—	4	1	—		
Phosphate 50°C	—	—	—	—	1		
Phosphoric Acid 10%	4	—	4	2	1		
Phosphoric Acid 25/50%	4	—	4	2	1		
Phosphoric Acid 50/80%	4	1	4	2	1		
Phosphorus Oxychloride	—	—	—	—	1		
Phosphorous Pentoxide 20°C	—	—	—	—	1		
Phosphorous Pentoxide	—	—	4	4	1		
Phthalic Acid	1	—	4	—	1		
Phtalic Anhydride	—	—	4	2	1		
Picric Acid	—	1	3	2	1		
Pickling solution	—	4	—	—	1		
Polyvinyl Acetate	—	1	—	—	1		
Potassium Bicarbonate	—	—	2	2	1		
Potassium Bichromate (30%)	—	—	4	4	1		
Potassium Bromide	1	1	2	2	1		
Potassium Carbonate 50%	1	—	2	2	1		
Potassium Chlorate	—	1	2	2	1		
Potassium Chloride	1	1	2	2	1		
Potassium Chromate 30%	—	1	—	—	1		
Potassium Cyanide 30%	1	1	2	2	1		
Potassium Ferricyanide 30%	—	—	2	2	1		
Potassium Fluoride	—	—	2	2	1		

CORROSION STRENGTH VALUES KORROSIONSBESTÄNDIGKEITSWERTE



1 = EXCELLENT 2 = GOOD 3 = INSUFFICIENT 4 = UNADVISABLE — = NO INFORMATION AVAILABLE	DE LR IN	EP DM	EA COR RO SION	HA ZAR D	VI T ON	PT FE	1 = SEHR GUT 2 = GUT 3 = NICHT VORGESCHLAGEN 4 = SCHLECHT — = FEHLENDE INFORMATIONEN	DE LR IN	EP DM	EA COR RO SION	HA ZAR D	VI T ON	PT FE
Potassium Hydroxide	—	—	2	2	1		Stannic Chloride	—	1	2	2	1	
Potassium Hydroxide 5-30%	—	1	4	—	1		Stannous Chloride	—	1	2	2	1	
Potassium Hydroxide 50-90%	—	1	2	4	1		Starci	—	2	2	—	1	
Potassium Hypochlorite 30°C	—	—	4	2	1		Steam 130°C	4	1	4	4	1	
Potassium Hypochlorite 90°C	—	—	4	—	1		Stearic Acid	1	—	2	—	1	
Potassium Iodide 70%	1	1	—	—	1		Suds	—	1	2	—	1	
Potassium Nitrate 80%	—	1	2	2	1		Sugarbeet Liquor	—	—	—	2	1	
Potassium Nitrate 1-5%	—	1	2	2	1		Sulphuric Acid 10-50%	3	1	3	1	1	
Potassium Oxalate 20%	—	—	—	—	1		Sulphuric Acid 60-70%	3	1	4	1	1	
Potassium Permanganate	—	1	4	3	1		Sulphuric Acid 80-100%	4	—	4	1	1	
Potassium Phosphate	—	—	1	1	1		Sulphurous Acid	3	—	4	2	1	
Potassium Sulphate 10%	1	1	2	2	1		Sulphamic Acid	—	1	—	—	1	
Potassium Sulphite	—	2	3	—	1		Sulphur 20°C	—	—	4	4	1	
Potassium Sulphite	—	—	—	4	1		Sulphur Chloride	—	—	4	2	1	
Propane	1	1	2	1	1		Swimming pool Water	—	1	2	—	1	
Propanol	—	—	2	2	1		T						
Propylene Oxide	—	—	4	—	1		Tannic Acid	1	—	4	3	1	
Propylene Glycol	—	—	2	2	1		Tar	1	4	4	2	1	
Pyridine	—	—	4	4	1		Tartaric Acid	1	—	2	2	1	
Pyrogalllic Acid	1	—	3	3	1		Tetraphosphoric Acid	—	—	—	—	1	
R							Tetrachydrofuran	—	—	4	4	1	
Resins	—	—	—	2	1		Tetraethyl Lead	—	—	4	2	1	
S							Thionyl Chloride	—	—	4	4	1	
Salicylic Acid	1	—	4	2	1		Toluene	1	4	4	2	1	
Salt Water	—	1	2	2	1		Tomato Juice	—	—	2	2	1	
Sea Water	1	1	2	2	1		Trichloroacetic Acid	—	—	4	2	1	
Sewage	—	2	2	2	1		Trisodium Phosphate	—	—	2	2	1	
Sewage	—	—	2	2	1		Tributyl Phosphate 30°C	—	—	4	4	1	
Silver Nitrate	1	1	2	2	1		Trichloroethylene	—	—	4	1	1	
Silicone Oil	—	—	2	2	1		Transformer Oil	—	—	2	2	1	
Sodium Acetate	1	1	—	4	1		Turpentine	1	4	2	2	1	
Sodium Bicarbonate	1	1	2	2	1		U						
Sodium Bichromate	—	—	—	2	1		Unleaded Petrol	1	—	2	2	1	
Sodium Bisulphite	1	1	2	2	1		Urea	—	—	4	1	1	
Sodium Borate	1	—	2	2	1		V						
Sodium Bromide	—	—	1	1	1		Various Esters	—	—	—	—	1	
Sodium Carbonate	1	—	2	2	1		Various Ethers 40°C	—	—	2	4	1	
Sodium Chlorate	—	1	2	2	1		Various Soaps	—	—	2	2	1	
Sodium Chlorite	—	—	—	—	1		Various Ketones	—	—	4	4	1	
Sodium Chloride	1	1	2	2	1		Vaseline	—	—	3	3	1	
Sodium Disulphate	—	—	2	2	1		Vegetable Oil	—	—	2	1	1	
Sodium Fluoride	—	1	—	—	—		Vinyl Acetate	—	—	4	2	1	
Sodium Hydroxide (Caustic Soda)	—	1	3	—	1		W						
Sodium Hypochlorite	1	1	4	2	1		Wet Chlorine Gas	—	1	4	2	1	
Sodium Hypochlorite	—	1	2	2	1		Wet Sulphurized Hydrogen	—	1	4	1	1	
Sodium Metaphosphate	—	—	2	2	1		Wet Sulphur Dioxide	1	1	2	4	1	
Sodium Nitrate	1	1	3	4	1		White Liquor	—	1	4	2	1	
Sodium Nitrite	—	—	—	—	1		Wine	—	—	2	2	1	
Sodium Perborate 10%	1	—	2	2	1		X						
Sodium Peroxide 10%	—	1	2	2	1		Xylene, Xylol	—	—	4	2	1	
Sodium Phosphate	—	—	2	2	1		Z						
Sodium Silicate	1	1	2	2	1		Zinc Chloride	1	1	2	2	1	
Sodium Sulphate	1	1	2	2	1		Zinc Nitrate	—	—	—	2	1	
Sodium Sulphite 10%	—	1	2	2	1		Zinc Sulphate 30%	—	1	2	2	1	
Sodium Sulphide 50%	1	1	2	2	1								
Sodium Thiosulphate	1	1	2	2	1								
Soft Water	1	1	1	—	1								
Spirit Vinegar	4	—	4	2	1								